

Flowcoat OP-T



Standard Colour Chart

	
Ivory	Yellow
	
Steel Blue	Mid Blue
	
Light Green	Dark Green
	
Tile Red	Light Grey
	
Steel Grey	Charcoal

The applied colours may differ slightly from the examples shown above.
Contact our customer services for a true colour sample or a special colour match.

Description;

High performance 4-6mm, solvent free, chemical resistant, trowel applied epoxy resin coating system. Different grades of slip resistance may be achieved by inclusion of graded aggregate between coats.

Typical Uses;

Flowcoat OP-T may be used as a hard wearing coloured floor coating in areas such as factories, warehouses, storerooms, plant rooms, light production and process areas.

Benefits;

- Chemical resistant
- Hard wearing
- Abrasion resistant
- Solvent free and low odour
- Attractive, light reflectant appearance
- Seamless and hygienic finish
- Low maintenance
- 4-6mm Thickness
- Impermeable
- Slip resistant finish can be tailored to specific client requirements

Model Specification

Product: Flowcoat OP-T

Finish: Gloss

Thickness: 4-6mm Dependant on specification

Colour: _____

Preparatory work and application in accordance with manufacturer's instructions.

Manufacturer: Flowcrete Australia Pty Ltd

Telephone: Customer Service - +61 7 3205 7115

Substrate Requirements

Concrete or screed substrate should be a minimum of 25N/mm², free from laitance, dust and other contamination. The substrate should be dry to 75% RH as per BS8204 and free from rising damp and ground water pressure.

Products Included in this System

Flowshield SL

Aggregate

Flowcoat SF41

For actual coverage rates, refer to the appropriate project specification.

Detailed application instructions are available upon request.

Coving

Coving forms an integral part of the flooring system. It creates a sealed finish between the floor and wall joint. Please refer to Flowtex F1 Coving Mortar for further information.

Installation Service

The installation should be carried out by a Flowcrete approved applicator with a documented quality assurance scheme. Obtain details of our approved contractors by contacting our customer service team or enquiring via our web site at www.flowcreteaustralia.com.au.

Environmental Considerations

The finished system is assessed as non-hazardous to health and the environment. The long service life and seamless surface reduce the need for repairs, maintenance and cleaning. Environmental and health considerations are controlled during manufacture and application of the products by Flowcrete staff and fully trained and experienced contractors.

Focus on the Floorzone

Flowcrete Australia Pty Ltd is a division of the Flowcrete Group, world leaders in specialist industrial and commercial flooring. Systems available include: underfloor heating systems, floor screeds, surface damp proof membranes, decorative floor finishes, seamless terrazzo, car park deck waterproofing and corrosion protection systems... to name just a few. Our corporate objective is to satisfy your flooring needs.

Technical Information

The figures that follow are typical properties achieved in laboratory tests at 20 °C and at 50% Relative Humidity.

Fire Resistance BS476:Part:7:
Surface spread of flame: Class1

Slip Resistance TRRL Pendulum Slip Test
Dry >40, Wet depends on specification

Textured systems are recommended to meet slip resistance value requirements for wet conditions and/or surface contaminants (wet or dry) - please contact our Technical Advisors for further details and specifications.

Thermal Resistance Tolerant up to 60 °C

Water Permeability Nil-Karsten test (impermeable)

Surface Hardness 180secs. Koenig Hardness Test

Chemical Resistance Contact Technical Department

Abrasion Resistance Taber Abrader:
80 mg loss per 1000 cycles
(1 kg load using CS10 wheels)
BS8204-2 Grade AR2

Compressive Strength > 60 N/mm² (BS6319)

Flexural Strength > 40 N/mm² (BS6319)

Tensile Strength > 15 N/mm² (BS6319)

Bond Strength Greater than cohesive strength
of 25 N/mm² concrete.
> 1.5 MPa.

Speed of Cure

	10°C	20°C	30°C
Light traffic	48 hrs	24 hrs	18 hrs
Full traffic	72 hrs	48 hrs	36 hrs
Full chemical cure	12 days	7 days	6 days

Aftercare - Cleaning and Maintenance

Clean regularly using a single or double headed rotary scrubber drier in conjunction with a mildly alkaline detergent.

Important Note

Flowcrete's products are guaranteed against defective materials and manufacture and are sold subject to its standard Terms and Conditions of Sale, copies of which can be obtained on request.

Further Information

To ensure you are specifying a fit for purpose flooring for your project please consult our Technical Advisors on the number below or visit our website to register your interest in specifying one of the most durable floors on the market.

Flowcrete Australia Pty Ltd
Brisbane Office (Regional)
Unit 2, 41 Deakin Street
Brendale QLD 4500
Tel: +61 7 3205 7115
Fax: +61 7 3205 3116
Email: australia@flowcrete.com
Flowcrete Australia is an RPM company

Sydney Office
Unit 1/12 Blackmore Road
Smeaton Grange NSW 2567
Tel: +61 2 4648 0397
Fax: +61 2 4648 0719