



Architectural Specification

Project Name: _____

System Name:

Deckshield ID Rapide

Description:

Deckshield ID Rapide is a rapid curing flexible MMA car park deck coating system, providing a colourful, watertight, hard wearing surface.

Thickness:

3mm

Colour: _____

Slip Resistant Rating: _____

Finish:

Textured

Preamble:

This specification assumes a concrete base >25 N/mm² compressive strength, application temperature 10-25°C. Substrate should be dry to 75% RH as per BS 8204-6. If above 75% RH contact Flowcrete Australia.

Surface Preparation:

Enclosed shotblasting, light scarification or coarse diamond grinding of concrete to remove any surface contaminants. Edges completed by vacuum controlled hand tools. All residues must be removed to provide a dry and dust free open textured surface.

Curing:

1 Hour Cure at 25°C.

Traffic:

Full traffic after 2 hours at 25°C.

Note:

Coving should be formed with Flowtex F1 Coving Mortar in conjunction with Deckshield Rapid Topcoat on vertical surfaces.

Products included in system

- Flowfast Primer
- Flowfast Flexible Binder
- Deckshield Bauxite/Oxide
- Deckshield Rapid Topcoat

Cleaning:

Please consult our Technical Advisory team 07 3205 7115 or email australia@flowcrete.com for specific cleaning and maintenance requirements.

Additional information

Please consult product Health & Safety, system, product and application data or contact our Technical Advisory team 07 3205 7115 or email australia@flowcrete.com

Any recommendation or suggestion relating to the use of the products made by Flowcrete Australia Pty Ltd., whether in its technical literature, or in response to a specific enquiry, or otherwise, is based upon data believed to be reliable, however the products and information are intended for use by customers having requisite skill and know-how in the industry and therefore it is for the customer to satisfy itself of the suitability of the products for its own particular use and it shall be deemed that the customer has done so at its sole discretion and risk.