

## Project Details

|              |                |
|--------------|----------------|
| Project Name |                |
| System Name  | Mondéco Rapide |

## Architectural Specification

### Mondéco Rapide

An innovative, rapid curing, seamless, resin-based decorative terrazzo floor finish which features Australia marble aggregates.

|                        |   |
|------------------------|---|
| <b>Thickness</b>       | Applied at 10mm, (ground down to 8mm).  |
| <b>Colour</b>          |   |
| <b>Slip Resistance</b> |   |
| <b>Testing</b>         | AS/ISO 9239.1<br>CHF Value 5.7 kW/m <sup>2</sup><br>Smoke Value <4% (Mean)  |
| <b>Finish</b>          | Semi Gloss / Gloss  |
| <b>Curing</b>          | Full Chemical Cure<br>2-3hrs @ 20°C   |
| <b>Traffic</b>         | Light traffic after 1 hr  |
| <b>Coving</b>          | Coving can form an integral part of the flooring system. It creates a sealed finish between the floor and wall joint. Please refer to Flowtex F1 Coving Mortar for further information. |

### Products Included In This System

|                |                          |
|----------------|--------------------------|
| <b>Layer 1</b> | Flowfast Primer          |
|                | Quartz 8/16 Mesh Scatter |
| <b>Layer 2</b> | Mondéco Rapide           |
| <b>Layer 3</b> | Mondéco Grout            |
| <b>Layer 4</b> | Mondéco Sealer           |
| <b>Layer 5</b> | Mondéco Sealer           |
| <b>Layer 6</b> | Mondéco Sealer           |

### Preamble

This specification assumes a concrete compressive strength greater than 25 N/mm<sup>2</sup>, application and curing temperatures of 10–35°C, the presence of an effective damp proof membrane below substrate and concrete moisture content less than 75% RH. If moisture content is above 75% RH, please contact Flowcrete Australia.

This specification must be read in conjunction with relevant product technical data sheets and the application of all materials is to be strictly in accordance with manufacturer's instructions

Please consult product health & safety, system, product and application data or contact our Technical Advisory team for further information.

Please note, when printed or saved externally, this document is uncontrolled and therefore may not be the latest version.

|                     |                               |
|---------------------|-------------------------------|
| <b>Manufacturer</b> | Flowcrete Australia Pty Ltd   |
| <b>Address</b>      | HQ - Unit 2, 41 Deakin Street |
| <b>Suburb</b>       | Brendale                      |
| <b>State</b>        | QLD                           |
| <b>Postcode</b>     | 4500                          |
| <b>Telephone</b>    | +61 7 3205 7115               |
| <b>Email</b>        | australia@flowcrete.com       |

## Surface Preparation

Surface preparation is to be completed by totally enclosed (light shot blasting) or coarse diamond grinding. All cementitious laitance must be removed to expose a sound substrate and provide a dry, dust free, open textured surface. All hard to reach areas and areas around the perimeter must be prepared using hand held preparation equipment.

Any damaged areas must be repaired with Flowfast F1 mortar. Consult Flowcrete prior to using an alternative repair mortar. Any rough or uneven areas must be made smooth with Flowfast SC (Flowfast Primer, Flowfast Binder, Sand/Flour). Consult Flowcrete prior to using an alternative MMA scratch coat.

## Cleaning

For specific cleaning and maintenance requirements, please consult our Technical Advisory team on **07 3205 7115** or email [australia@flowcrete.com](mailto:australia@flowcrete.com).

## Note

Any recommendation or suggestion relating to the use of the products made by Flowcrete Australia Pty Ltd., whether in its technical literature, or in response to a specific enquiry, or otherwise, is based upon data believed to be reliable, however the products and information are intended for use by Customers having requisite skill and know-how in the industry and therefore it is for the Customer to satisfy itself of the suitability of the products for its own particular use and it shall be deemed that the Customer has done so at its sole discretion and risk.